

제품 규격

Item	Method	Unit	Gr.III					
			4cSt		6cSt		8cSt	
			Spec.	Typical	Spec.	Typical	Spec.	Typical
ASTM Color	ASTM D1500		Max 0.5	L0.5	Max 0.5	L0.5	Max 0.5	L0.5
Viscosity @ 40°C	ASTM D445	mm ² /s	-	20.51	-	37.31	-	46.07
Viscosity @ 100°C	ASTM D445	mm ² /s	4.0~4.4	4.36	5.5~6.5	6.43	7.0~8.5	7.38
Viscosity Index	ASTM D2270		Min 120	123	Min 120	124	Min 120	123
Pour Point	ASTM D6749	°C	Max -15	-18	Max -15	-18	Max -15	-18
Flash Point, COC	ASTM D92	°C	Min 200	220	Min 200	233	Min 200	247
Noack Volatility	ASTM D5800	wt%	-	15.4	-	7.6	-	4.5
Aromatics	ASTM D3238	wt%	Max 1.0	0.0	Max 1.0	0.0	Max 1.0	0.0
CCR	ASTM D189	wt%	Max 0.01	L0.01	Max 0.01	L0.01	Max 0.01	L0.01
TAN	ASTM D974	mgKOH/g	Max 0.01	0.003	Max 0.01	0.004	Max 0.01	0.004